





POLAR
Möbelstoff

 **svensson**



3035



3135



3224



3334



3454




3552




4232




4342




4443




4544




4560




4562




4754



4833




5560




5671




5734



5925



6035



6061

POLAR

Möbelstoff

Breite: 140 cm
Gewicht: 350 G/M²
Material: Wolle 85%
 Polyamid 15%

Color fastness:
Against dry rubbing according to
EN ISO 105-X12:
 - ≥4 (Scale 1-5)
Gegen Licht nach EN ISO 105-B02
 - ≥5-7 (Skala 1-8)
Against wet rubbing according to
EN ISO 105-X12:
 - ≥3-4 (Scale 1-5)

Scheuerfestigkeit:
Martindale (Nach: EN ISO 12947-2):
 - 100000 Touren

Schwerentflammbarkeit:
 - EN 1021-1, 2- IMO FTP Code 2010:
 - IMO FTP Code 2010: Part 8

Wartungsanweisungen:



For further information:


Svensson
 511 82 Kinna, Sweden

T: +46 320 20 92 00
 F: +46 320 21 10 10
 E: info@ludvigsvensson.com






6630




6634



6851



8200



8800

POLAR

Möbelstoff

Breite: 140 cm
Gewicht: 350 G/M²
Material: Wolle 85%
Polyamid 15%

Color fastness:
Against dry rubbing according to EN ISO 105-X12:
- ≥4 (Scale 1-5)
Gegen Licht nach EN ISO 105-B02
- ≥5-7 (Skala 1-8)
Against wet rubbing according to EN ISO 105-X12:
- ≥3-4 (Scale 1-5)

Scheuerfestigkeit:
Martindale (Nach: EN ISO 12947-2):
- 100000 Touren

Schwerentflammbarkeit:
- EN 1021-1, 2- IMO FTP Code 2010:
- IMO FTP Code 2010: Part 8

Wartungsanweisungen:



For further information:

Svensson
511 82 Kinna, Sweden

T: +46 320 20 92 00
F: +46 320 21 10 10
E: info@ludvigsvensson.com

